

SPECIFICATION CONTROL DRAWING

SCD

55/0314

Title WIRE, RADIATION-CROSSLINKED, MODIFIED ETFE-INSULATED,
ULTRA LIGHTWEIGHT, OUTER SPACE, 600 VOLT

Date 9-27-18

Revision J

This specification sheet forms a part of the latest issue of Raychem Specification 55/.

CONDUCTOR - SILVER-COATED HIGH-STRENGTH
COPPER ALLOY

INSULATION - RADIATION-CROSSLINKED,
MODIFIED ETFE




TABLE I. CONSTRUCTION DETAILS

PART NUMBER 1/	WIRE SIZE (AWG)	CONDUCTOR STRANDING (number x AWG)	DIAMETER OF STRANDED CONDUCTOR (inch)		FINISHED WIRE		
			MINIMUM	MAXIMUM	MAXIMUM RESISTANCE AT 20°C (ohms/1000 ft.)	DIAMETER (inch)	MAXIMUM WEIGHT (lbs/1000 ft.)
55/0314-30-*	30	7 x 38	.0110	.0120	117.4	.0195 ± .0015	.52
55/0314-28-*	28	7 x 36	.0140	.0150	74.4	.0225 ± .0015	.76
55/0314-26-*	26	19 x 38	.0175	.0191	44.8	.0274 ± .0017	1.22
55/0314-24-*	24	19 x 36	.0225	.0241	28.4	.0322 ± .0017	1.79
55/0314-22-*	22	19 x 34	.0285	.0301	17.5	.0390 ± .0017	2.70
55/0314-20-*	20	19 x 32	.0365	.0385	10.7	.0495 ± .0017	4.27
55/0314-18-*	18	19 x 30	.0452	.0476	6.8	.0590 ± .0017	6.56
55/0314-16-*	16	19 x 29	.0514	.0538	5.3	.0665 ± .0019	8.33

TABLE II. PERFORMANCE DETAILS

PART NUMBER 1/	CROSSLINKED VERIFICATION - BEND TESTING	
	MANDREL DIAMETER (inch) (± 3%)	WEIGHT (lb) (± 3%)
55/0314-30-*	.250	.063
55/0314-28-*	.250	.063
55/0314-26-*	.375	.063
55/0314-24-*	.375	.125
55/0314-22-*	.500	.188
55/0314-20-*	.500	.250
55/0314-18-*	.500	.250
55/0314-16-*	.750	.375

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.
TE Connectivity also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE
ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.





WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C

Maximum continuous conductor temperature

VOLTAGE RATING: 600 volts (rms) at sea level

COLOR: White preferred

CONCENTRICITY: 80% (minimum)

CROSSLINKED VERIFICATION: 300 ± 3°C for 1 hour

IDENTIFICATION AND COLOR STRIPING DURABILITY:

125 cycles (250 strokes) (minimum), 500 g weight

INSULATION ELONGATION: 50% (minimum)

INSULATION FLAWS:

Spark Test, 1.5 kV (rms) (30-24 AWG)

3.0 kV (rms) (22-16 AWG)

Impulse Dielectric Test, 6.0 kV (peak)

INSULATION THICKNESS: .004 in. (nominal)

RADIATION RESISTANCE: 500 megarads

SHRINKAGE: 230 ± 3°C for 1 hour, 0.125 in. (maximum) in 12 inches

VACUUM STABILITY:

Total Mass Loss (TML), 1.00% (maximum)

Volatile Condensable Material (VCM): 0.10% (maximum)

VOLTAGE WITHSTAND (Post Environmental): 1500 volts (rms), 60 Hz, 5 minutes

1/ PART NUMBER:

The "*" in the part numbers in Tables I and II shall be replaced by a color code designator.

Example: AWG 28, white: 55/0314-28-9

AWG 28, white with a black stripe: 55/0314-28-90