SPECIFICATION CONTROL DRAWING

44A118X


TITLE EIGHT CONDUCTOR CABLE, SHIELDED, JACKETED, GENERAL PURPOSE, 600 VOLT Revision

D

This specification sheet forms a part of the latest issue of Raychem Specification 44.

Date

11-4-10




FILAMENT BINDER AS REQUIRED

TABLE I. CABLE CONSTRUCTION DETAILS									
PART NUMBER <u>1</u> /	CONDUCTOR SIZE (AWG)	SHIELD SIZE (AWG)	JACKET THICKNESS (in.)		OUTSIDE DIAMETER (in.)		MAXIMUM WEIGHT		
			MINIMUM	NOMINAL	NOMINAL	MAXIMUM	(lbs/1000 ft.)		
44A118X-26-*	26	36	.006	.008	.148	.167	22.5		
44A118X-24-*	24	36	.007	.009	.169	.192	30.4		
44A118X-22-*	22	36	.007	.009	.192	.219	40.6		
44A118X-20-*	20	36	.007	.009	.218	.249	55.2		
44A118X-18-*	18	36	.007	.009	.250	.287	77.7		
44A118X-16-*	16	36	.008	.010	.275	.315	96.1		
44A118X-14-*	14	36	.008	.010	.330	.379	142.		
44A118X-12-*	12	36	.010	.012	.396	.455	214.		

TABLE II. CABLE PERFORMANCE DETAILS								
PART NUMBER <u>1</u> /	BEND TESTING							
	MANDREL DIAMETE (inch) (±3%)	ER	WEIGHT (lb) (±3%)					
	LIFE CYCLE, IMMERSION AND ACCELERATED AGING	COLD BEND	LIFE CYCLE, IMMERSION AND ACCELERATED AGING	COLD BEND				
44A118X-26-*	6.00	6.00	1.00	6.00				
44A118X-24-*	6.00	6.00	1.50	6.00				
44A118X-22-*	6.00	6.00	1.50	12.0				
44A118X-20-*	6.00	6.00	1.50	12.0				
44A118X-18-*	6.00	6.00	2.00	12.0				
44A118X-16-*	10.0	10.0	2.00	12.0				
44A118X-14-*	10.0	10.0	4.00	36.0				
44A118X-12-*	18.0	18.0	4.00	36.0				

NOTE: Nominal values are for information only. Nominal values are not requirements.



© 2010 Tyco Electronics Corporation. All rights reserved.



SCD

CABLE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 150°C Maximum continuous conductor temperature VOLTAGE RATING: 600 volts (rms) at sea level ACCELERATED AGING: 300 ± 3°C for 6 hours BLOCKING: 150 ± 3°C for 6 hours DIELECTRIC WITHSTAND: 2500 volts (rms), 60 Hz, 1 minute FLAMMABILITY: 30 seconds (maximum); 3 in. (maximum); no flaming of facial tissue IMMERSION: Diameter increase 5% (maximum), no cracking, no dielectric breakdown JACKET COLOR: White preferred JACKET CONCENTRICITY: 70% (minimum) JACKET ELONGATION AND TENSILE STRENGTH: Elongation, 200% (minimum) Tensile Strength, 4000 lbf/in² (minimum) JACKET FLAWS: Spark Test, 1.5 kV (rms) Impulse Dielectric Test, 6.0 kV (peak) LIFE CYCLE: 200 ± 3°C for 168 hours LOW TEMPERATURE-COLD BEND: -65 ± 2°C for 4 hours SHIELD COVERAGE: 85% (minimum) VOLTAGE WITHSTAND (Post Environmental): 1000 volts (rms), 60 Hz, 1 minute

PART NUMBER:

The "X" in the part numbers on page 1 shall be replaced by the applicable conductor material designator as follows:

- 1 tin-coated copper
- 2 silver-coated copper
- 3 nickel-coated copper
- 4 silver-coated high-strength copper alloy (AWG's 26 16 only)
- 6 nickel-coated high-strength copper alloy (AWG's 26 20 only)

The "*" in the part numbers on page 1 shall be replaced by color code designators with a slash separating the component wire colors and a dash separating the component wire colors from the jacket color. Colors shown do not necessarily reflect the sequence of manufacturing.

1/ Example: AWG 20, tin-coated copper wires, black, brown, red, orange, yellow, green, blue and violet component wires; white jacket: 44A1181-20-0/1/2/3/4/5/6/7-9

1/ See footer section on page 1