SPECIFICATION CONTROL DRAWING

77 OHM, AWG 24, 19 STRANDS OF AWG 36,

7724M1664

Date: Α Revision:




CONSTRUCTION DETAILS **ELECTRICAL CHARACTERISTICS**

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200.

OPTIMIZED SHIELD, DATA BUS CABLE, MIL-STD-1553

DIMENSIONS ARE NOMINAL VALUES IN INCHES. UNLESS OTHERWISE



.113

.129

(nominal)

.134

(maximum)

CONDUCTORS

AWG 24, 19 Strands of AWG 36, Silver-Coated High-Strength Copper Alloy

DIELECTRICS

Radiation-Crosslinked, Modified ETFE Colors - Light Blue/White

FILLERS

Radiation-Crosslinked, Modified ETFE

SHIELD

AWG 38, Silver-Coated Copper, Optimized

JACKET

Radiation-Crosslinked, Modified ETFE

CHARACTERISTIC IMPEDANCE 77 ± 5 ohms. Method C at 1 MHz

MUTUAL CAPACITANCE 30.0 pF/ft. (maximum)

ATTENUATION 1.4 dB/100 ft. (maximum) at 1 MHz

SURFACE TRANSFER IMPEDANCE 80 milliohms/meter (maximum)

from 10 kHz to 100 MHz

ADDITIONAL REQUIREMENTS

COMPONENT WIRE PRIOR TO CABLING (Test procedures per SAE AS22759)

CONDUCTOR RESISTANCE 26.5 ohms/1000 ft. (nominal)

CROSSLINKING PROOF TEST 300 ± 3°C for 1 hour, .625 inch mandrel,

.375 lb, 2.5 kV dielectric test

INSULATION (DIELECTRIC)

ELONGATION 50% (minimum) TENSILE STRENGTH 5000 lbf/in2 (minimum)

INSULATION FLAWS

SPARK TEST 3.0 kV (rms) **IMPULSE TEST** 8.0 kV (peak)

INSULATION RESISTANCE 5000 megohms for 1000 ft. (minimum) LOW TEMPERATURE-COLD BEND $-65 \pm 3^{\circ}$ C for 4 hours, .750 inch mandrel,

1.00 lb, 2.5 kV dielectric test

SHRINKAGE $200 \pm 3^{\circ}$ C for 1 hour,

.125 inch (maximum) in 12 inches

FINISHED CABLE

(Test procedures per NEMA WC 27500, unless otherwise specified)

BLOCKING 200°C for 6 hours

CABLE LAY LENGTH .75 inch (minimum), 1.25 inches (maximum) CROSSLINKED VERIFICATION 300 ± 5°C for 6 hours, 6.00 inch mandrel

FLAMMABILITY 3 seconds (maximum); 3 inches (maximum); (Method B of Spec 1200)

no flaming of facial tissue

ELONGATION 50% (minimum) TENSILE STRENGTH 5000 lbf/in2 (minimum)

JACKET FLAWS

1.0 kV (rms) SPARK TEST **IMPULSE TEST** 6.0 kV (peak) JACKET THICKNESS .008 inch (nominal)

LOW TEMPERATURE-COLD BEND -55 ± 5°C for 4 hours, 6.00 inch mandrel

VOLTAGE WITHSTAND

(DIELECTRIC)

1500 volts (rms)

Designate outer jacket color with a dash number in accordance with MIL-STD-681. Unless otherwise specified, outer jacket color will be white (designated by a "-9" appended to the part number, e.g. 7724M1664-9).

Other codes and suffixes may be added to the part number, as necessary, to capture any additional requirements imposed by the purchase order.

WEIGHT

15.9 lbs/1000 ft. (maximum)

ENGINEERING REFERENCE

TEMPERATURE RATING 200°C (maximum)

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice. Tyco Electronics Corporation also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

Cheminax, Raychem, TE Connectivity, TE connectivity (logo), and TE (logo) are trademarks.

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN.

