

## WIRE, MODIFIED FLUOROPOLYMER INSULATED, T4 (3000 Hours @ 150°C) 50 VOLT, LIGHTWEIGHT The complete requirements for procuring the wire described herein shall consist of this document and the issue in effect of Raychem Specification WSD 1223

Insulation -Radiation Crosslinked, Modified, Polyalkene Blend

Conductor -

**Bare Copper** 

0890	Ð.			

Jacket -Radiation Crosslinked Modified PVF<sup>2</sup>

Part	Conductor	Maximum	Conductor	FINISHED WIRE							
Description	Cross	Conductor	Diameter	Conductor		Overall	Di	ameter (m	m)	Approximate	Copper
	Sectional	Stranding	(mm)	Resistance		Insulation	Lower		Upper	Weight Per	Weight
	Area	No./diam.		@20°C (0	Ohms/km)	Thickness	Spec	Target	Spec	Unit Length	Information
	(mm²)	(mm)	Max.	Min.	Max.	Min. (mm)	Limit		Limit	(kg/km)	only (g/m)
ACW0219-0.35-*	0.35	7/0.26	0.80	47.8	52.0	0.20	1.2	1.3	1.4	4.5	3.05
ACW0219-0.50-*	0.50	19/0.19	1.00	34.1	37.1	0.22	1.4	1.5	1.6	6.0	4.40
ACW0219-0.75-*	0.75	19/0.23	1.20	22.7	24.7	0.24	1.7	1.8	1.9	9.4	6.50
ACW0219-1.00-*	1.00	19/0.26	1.35	17.0	18.5	0.24	1.9	2.0	2.1	11	8.50
ACW0219-1.25-*	1.25	19/0.285	1.47	13.7	14.9	0.22	2.1	2.2	2.3	13.5	10.60
ACW0219-1.50-*	1.50	19/0.32	1.70	11.7	12.7	0.24	2.2	2.3	2.4	16	12.6
ACW0219-2.50-*	2.50	19/0.41	2.15	7.00	7.60	0.28	2.7	2.85	3.0	25	21.0
ACW0219-4.0-*	4.00	61/0.29	2.50	4.42	4.70	0.32	3.4	3.55	3.7	40	36.0
ACW0219-6.0-*	6.00	61/0.36	3.02	2.91	3.10	0.32	4.0	4.15	4.3	61	54.0
ACW0219-10.0-*	10.0	91/0.38	4.00	1.70	1.82	0.48	5.5	5.75	6.0	104	95.0

COLOUR CODE: The '\*' in the part number shall be replaced by a standard numerical colour code designator. Additional number after base colour indicates stripe.

e.g. ACW0219-0.50-96 White base colour with blue stripe.

Where stripes are required, the wire carries two co-extruded longitudinal stripes of the same colour. The individual stripe width is a minimum of 10% of the wire circumference with an overall stripe coverage of 30% maximum

## Co-extruded longitudinal stripes are not available on CSA size 10.0mm.

**ADDITIONAL** Insulation Flaws:

**REQUIREMENTS:** 

TESTING: 100% Spark Test on Finished wire of 5.0 kV High Frequency AC RMS or equivalent.

All wire to be marked, with the following exceptions, Wire for: MARKING

component use,

Spooling instruction S50 and SMP-SP.

Frequency of mark:

Repeat mark along length of wire at a distance of 165 mm between the start of one mark and the start of another.

Colour of mark:

□ All black base products regardless of stripe colour are to be marked using white ink.

□ All other base colours except black regardless of stripe colour are to be marked using black ink.

NOT TO SCALE MARK DETAIL:

		1	65mm ———					
$\stackrel{\cdot}{\circ}$ $\circ$ $\circ$	000	$\circ \circ \circ$	000	0 0	0	000	000	000
0 0	0 0	0 0	0 0	0	0	0 0	0 0	0 0
$\circ \circ \circ$	000	000	$\circ \circ \circ$	0 0	0	000	$\circ \circ \circ$	000

## APPROVAL:

araday Road Dorcan SWINDON

Electronic approval - no signatures will appear.

TE Connectivity is a trading name of Tyco Electronics UK Ltd, Which is registered in England and Wales, number 550926. Registered office: Faraday Road, Dorcan, Swindon, SN3 5HH Website : www.te.com Tyco Electronics UK Ltd. SN3 5HH Tel: +44 (0)1793 528171 Fax: +44 (0)1793 572516

This drawing and the information set forth hereon are the property of Tyco Electronics UK Ltd, and are to be held in trust and confidence. Publication duplication, disclosure or use for any purpose not expressly authorised in writing by Tyco Electronics UK Ltd is prohibited. Raychem, TE Connectivity and TE Connectivity logo are trademarks.

This specification sheet takes precedence over documents referenced herein. As Tyco Electronics UK Ltd. reserve the right to make changes in construction without notice please contact Tyco Electronics UK Ltd to ensure that this document is nced documents shall be of the issue in effect the latest issue. Referenced on date of invititaion for bid